



Base Coat Stucco – Pump Grade

No. 1139-86

Product Description:

Basic Use: QUIKRETE® Base Coat Stucco – Pump Grade is a Portland cement based stucco, designed to be used as the scratch and/or brown coat in a 3-coat stucco application, or the first coat in a 2-coat application. This product contains special additives which prevent premature loss of mixing water and provide increased workability.

Packaging: Each 80 pound (36.3 Kg) bag will yield approximately 0.83 cu ft (23 L) of material.

Physical Properties

QUIKRETE® Base Coat Stucco – Pump Grade meets ASTM C926 requirements for Portland cement-based plaster.

Mixing

Blend approximately 1.5 gal (5.7 L) of water per 80 lb (36.3 kg) bag. Place the water in the mixer, and then slowly add the QUIKRETE® Base Coat Stucco – Pump Grade. Mix for 2 - 3 minutes, or until a trowelable consistency is achieved. Add additional amounts of water if necessary; do not exceed 7 quarts (6.6 L) per 80 pound bag.

Application

QUIKRETE® Base Coat Stucco – Pump Grade is intended for use over galvanized expanded metal lath or solid bases such as masonry, cast-in-place or pre-cast concrete. Installation over these surfaces shall be in accordance with ASTM C926 and local building codes. QUIKRETE® Base Coat Stucco – Pump Grade may be applied with a trowel or sprayer according to typical stucco techniques.

- Mix only as much QUIKRETE® Base Coat Stucco as can be applied in 1 hour. Variation in water addition will affect color uniformity
- Do not apply additional water during application. Proper rewetting of base coats and finish treatment will eliminate the need for additional water. Avoid overlapping fresh stucco over previously dried areas as this will result in a lack of color uniformity

Curing

Provide sufficient moisture to permit continuous hydration of the cementitious materials and minimize

cracking. Under normal conditions, moist curing is accomplished by applying a fine fog spray of water generally twice daily in the morning and evening. Care must be exercised to avoid erosion damage to plaster surfaces. This procedure should be repeated for several days following stucco application. During hot and dry conditions, additional precautions may be necessary, including more frequent misting or the erection of barriers to deflect sunlight and wind.

Note – QUIKRETE® Finish Coat Stucco (#1201) can be applied over QUIKRETE® Base Coat Stucco – Pump Grade in accordance with ASTM C926 and local building codes.

Precautions

Do not apply when temperatures are expected to fall below 40 degrees F (4 degrees C) or rise above 100 degrees F (38 degrees C) within a 24 hour period. Do not use polymeric admixtures with this product, as excessive air entrainment may result.

Warranty

The QUIKRETE® Companies warrant this product to be of merchantable quality when used or applied in accordance with the instructions herein. The product is not warranted as suitable for any purpose or use other than the general purpose for which it is intended. Liability under this warranty is limited to the replacement of its product (as purchased) found to be defective, or at the shipping companies' option, to refund the purchase price. In the event of a claim under this warranty, notice must be given to The QUIKRETE® Companies in writing. This limited warranty is issued and accepted in lieu of all other express warranties and expressly excludes liability for consequential damages.

The QUIKRETE® Companies, Inc.

One Securities Centre
3490 Piedmont Road, Suite 1300
Atlanta, GA 30305
404.634.9100