



Fiber Reinforced Deck Mix

No. 1251-80, -81

BASIC USE

QUIKRETE Fiber Reinforced Deck Mix (#1251-80) is an air-entrained, normal-setting, fiber-reinforced material designed to repair highways, bridge decks, concrete parking lots, and other concrete surfaces as a patching material for commercial applications at a thickness of 2" (51 mm) – 2 feet (12.7 - 610 mm). QUIKRETE Fiber Reinforced Deck Mix is fortified with an integral corrosion inhibitor. A polymer-modified version (#1251-81) is also available.

COMPOSITION & MATERIALS

QUIKRETE Fiber Reinforced Deck Mix is made from specially blended cement, fibers, carefully graded aggregates and additives approved for use in structural concrete. The product is air entrained and contains other additives to promote superior durability, high strength, and long working time.

YIELD

One 80-pound (36.3 kg) bag of QUIKRETE Fiber Reinforced Deck Mix will yield approximately 0.6 cu ft (17 L).

LIMITATIONS

• During extremely hot or dry conditions, cold water should be used to maintain mix at a moderate placement temperature

APPLICABLE STANDARDS

ASTM International

- ASTM C 39 Standard Test Method for Compressive Strength of cylindrical Concrete Specimens
- ASTM C 231 Standard Test Method for Air Content of Freshly Mixed Concrete by the Pressure Method
- ASTM C882 Standard Test Method for Bond Strength of Epoxy-Resin Systems Used With Concrete By Slant Shear

PHYSICAL/CHEMICAL PROPERTIES

QUIKRETE Fiber Reinforced Deck Mix when tested in accordance with ASTM procedures provides typical results as listed in Table 1.

TABLE 1
Fiber Reinforced Deck Mix Physical Properties

Compressive Strength (ASTM C39)	
24 Hours	1800psi (12.4 MPa)
3 Days	3000psi (20.7 MPa)
7 Days	4200psi (29.0 MPa)
28 Days	6000psi (41.4 MPa)
Air Content (ASTM C231)	
	5% - 8%
Shear Bond Strength (ASTM C882)*	
	2500 psi (17.2 MPa)

*Shear bond strength calculated using the cross-sectional area of the specimen

MIXING

The product will require approximately 3 quarts (2.8 L) of water per 80 pounds (36.3 kg) of product. Add approximately 90% of the expected water then add the dry material. Adjust slump with additional water to achieve a slump of 4-7" (100-175 mm). Mix until a uniform product is obtained. Do not exceed 4.5 quarts (4.3 L) per 80 pound bag.

PLACING

- The forms and substrate should be thoroughly dampened but do not leave puddles
- Fill the forms completely working from one end to the other. Avoid partial depth lifts, which could result in cold joints
- Consolidate the material using hand tamping and/or chopping with a shovel. It is particularly important to compact around the edges of the forms or patches
- Screed the surface, and then apply a trowel or broom finish as desired

The QUIKRETE® Companies, Inc.

One Securities Centre
3490 Piedmont Road, Suite 1300
Atlanta, GA 30305
404.634.9100

CURING

Proper curing increases the strength and durability of concrete repair materials. QUIKRETE Concrete Sealer (#8800) provides the easiest and most convenient method of curing. Apply by spray, brush or roller, when the surface is hard, following the final finishing operation. The surface may be damp, but not wet, when applying the curing compound. Under hot, dry and windy placing conditions, all concrete tends to lose moisture unevenly and may develop plastic shrinkage cracks. The use of sheeting, monomolecular films (either sprayed or rolled on), as well as application of a very fine fog spray of water, has been quite successful in arresting shrinkage cracking.

Warranty

The QUIKRETE® Companies warrant this product to be of merchantable quality when used or applied in accordance with the instructions or applied in accordance with the instructions herein. The product is not warranted as suitable for any purpose or use other than the general purpose for which it is intended. Liability under this warranty is limited to the replacement of its product (as purchased) found to be defective, or at the shipping companies' option, to refund the purchase price. In the event of a claim under this warranty, notice must be given to The QUIKRETE® Companies in writing at Atlanta, GA 30305. The limited warranty is issued and accepted in lieu of all other express warranties and expressly excludes liability for consequential damages.

The QUIKRETE® Companies, Inc.

One Securities Centre
3490 Piedmont Road, Suite 1300
Atlanta, GA 30305
404.634.9100