

COMMERCIAL GRADE PERMANENT BLACKTOP REPAIR

PRODUCT NO. 1701-59, -62

DIVISION 32

Flexible Paving Repair
32 01 17

PRODUCT DESCRIPTION

QUIKRETE® Permanent Blacktop Repair is a specially formulated high performance asphalt cold patch material for repairing potholes and cracks over 1" (25.4 mm) wide in asphalt pavements.

PRODUCT USE

QUIKRETE® Permanent Blacktop Repair is suitable for use on roads, driveways and walkways. The product contains new modifier technology which provides superior placement and bonding characteristics and produces a virtually permanent repair, even in cold, damp conditions.

SIZES

• QUIKRETE® Permanent Blacktop Repair - 50 lb (22.7 kg) and 60 lb (27.2 kg) bags

YIELD

• Each 50 lb (22.7 kg) bag will yield approximately 0.5 ft³ (14.2 L) when properly compacted and will cover an area of approximately 6 ft² (0.56 m²) when placed at a thickness of 1" (25.4 mm).
• Each 60 lb (27.2 kg) bag will yield approximately 0.60 ft³ (17 L) when properly compacted and will cover an area of approximately 7.2 ft² (0.67 m²) when placed at a thickness of 1" (25.4 mm).

TECHNICAL DATA

APPLICABLE STANDARDS

ASTM International

D448 Standard Classification for Sizes of Aggregate for Road and Bridge Construction

Note – QUIKRETE® Permanent Blacktop Repair is prepared from aggregate which complies with the open graded #9 or #89 size requirements in accordance with ASTM D448. It can be modified to meet specific requirements of State Departments of Transportation.

INSTALLATION

PREPARATORY WORK

Square cut the vertical sides of the hole to provide for proper confinement of the patch. Remove all loose material. Sweep the area thoroughly. In some cases, it may be desirable to further clean the surface with QUIKRETE® Concrete and Asphalt Cleaner. Be sure to rinse thoroughly. Do not apply QUIKRETE® Permanent Blacktop Repair in standing water.



APPLICATION

Follow these procedures when applying QUIKRETE® Permanent Blacktop Repair:

- It is important to square the vertical edges of the hole
- Fill the hole with QUIKRETE® Permanent Blacktop Repair to a height of 1/2" (12.7 mm) above the surrounding area. Do not apply less than 1" (25.4 mm) thick. Jobs requiring more than 1" (25.4 mm) of material in depth must have material applied in 1" (25.4 mm) lifts, where each lift is adequately compacted.
- Compact to a level surface with a tamper. (Patch may be covered with a piece of plywood or plastic and driven over with the front wheel of a car to further pack material.)
- Traffic can begin after satisfactorily leveling and compacting

PRECAUTIONS

Apply QUIKRETE® Permanent Blacktop Repair at a depth of 1" - 3" (25.4 - 76 mm). Apply in 1" (25.4 mm) lifts so that adequate compaction of each layer can be accomplished before more material is added. The product is not designed for curbs or other unconfined areas. Restrict the size of the repair to an area of approximately 3' x 3' (0.9 x 0.9 m). Resurfacing can only be done using a 1 - 3 ton (908 - 2724 kg) vibratory roller or 5 ton (4540 kg) regular roller.

Take the following precautions when using QUIKRETE® Permanent Blacktop Repair:

- Avoid getting Blacktop Repair on hands or clothing
- Avoid dry turning tires on patched area for at least 24 hours (longer in cold weather)
- Allow patch to cure at least 30 days (preferably up to 90 days) before applying QUIKRETE® Traffic Top or other driveway sealer
- Do not use for resurfacing paved areas

WARRANTY

The QUIKRETE® Companies warrant this product to be of merchantable quality when used or applied in accordance with the

instructions herein. The product is not warranted as suitable for any purpose or use other than the general purpose for which it is intended. Liability under this warranty is limited to the replacement of its product (as purchased) found to be defective, or at the shipping companies' option, to refund the purchase price. In the event of a claim under this warranty, notice must be given to The QUIKRETE® Companies in writing. This limited warranty is issued and accepted in

lieu of all other express warranties and expressly excludes liability for consequential damages.

The QUIKRETE® Companies
One Securities Centre
3490 Piedmont Rd., NE, Suite 1300, Atlanta, GA 30305
(404) 634-9100 • Fax: (404) 842-1425

** Refer to www.quikrete.com for the most current technical data, MSDS, and guide specifications*

