

**NEW!****COMMERCIAL GRADE  
QUIKRETE®**

# ANCHORING EPOXIES

## **FastSet™ ANCHORING EPOXY**

**No. 8620-30**

Fast Setting, two component structural epoxy with a working time of 4-5 minutes. Non-sag, solvent-free, low odor formula. Concrete gray color.

**Use for:**

- Anchoring bolts, threaded rods, railings and rebar dowels into concrete and masonry.
- Vertical or horizontal applications.
- Sets in sub-freezing temperatures.

<b>Set Time</b>	4-5 minutes
<b>Cure Time</b>	2 hours



Item No.	Package Size	Metric	Case Quantity	UPC
8620-30	8.6 oz	255 mL	12/case	0-39645-86210-0

## **High Strength ANCHORING EPOXY**

**No. 8620-31**

High strength, two component structural epoxy with an extended working time of 15 minutes. Formulated to allow for adequate placement time. Non-sag, solvent-free, low odor formula. Concrete gray color.

**Use for:**

- Heavy duty applications
- Anchoring bolts, threaded rods, railings, rebar and dowels into concrete and masonry.
- Horizontal applications.

<b>Set Time</b>	15 minutes
<b>Cure Time</b>	2 hours



Item No.	Package Size	Metric	Case Quantity	UPC
8620-31	8.6 oz	255 mL	12/case	0-39645-86211-7

**Cartridge Instructions:** 1) Remove plastic cap from the tip of the cartridge. 2) Screw static mixer nozzle onto the cartridge. 3) Place the cartridge into a caulk gun. 4) Dispense adhesive until a consistent gray color is achieved.

**Directions:** Dispense the epoxy from the bottom of the hole while withdrawing nozzle. Fill the hole approximately 1/2 of the hole depth. Insert threaded rod or rebar to the bottom of the hole while turning clockwise. Leave undisturbed until a minimum cure time has passed.