



Crack Resistant Concrete Mix

Product No. 1006-80



QUIKRETE® Crack Resistant Concrete Mix is a 4000 psi (27.6 MPa) construction grade blend of portland cement, air-entraining admixture, and special alkali-resistant special reinforcing fibers.

- Significantly reduces cracking from drying shrinkage
- Designed for use in structural concrete applications
- Superior workability
- Air entrained for improved freeze-thaw durability
- Provides greater impact resistance
- Eliminates the need for wire mesh in typical slab-on-grade concrete applications (*check your local building codes*)

USE FOR:

- Driveways
- Floors
- Patios
- Walkways
- Sidewalks

Exceeds Compressive Strength ASTM C-387

7 Days - 3,500 PSI (24.1 MPa)

28 Days - 4,000 PSI (27.6 MPa)

Crack Resistant Concrete Mix Calculator

Number of bags required

Square Feet	SLABS					
	2	5	10	25	50	100
(M ²)	(0.2)	(0.5)	(0.9)	(2.3)	(4.7)	(9.3)
4" (100mm) Thick Slab - # of 80 lb (36.3kg) bags	1	3	5	13	25	50
6" (150mm) Thick Slab - # of 80 lb (36.3kg) bags	2	4	8	19	38	75

All yields are approximate and do not allow for waste or uneven sub-grade, etc.

