


Self-Consolidating Core-Fill Grout

Product No. 1585-06



Portland cement based highly fluid grout specifically designed to fill masonry block cores without segregation. Exceeds 4000 psi at 28 days.

- Eliminates the need for vibrating.
- Complies with ASTM C-476 at a 24 -28" (600-700 mm) slump flow.
- Contains 3/8" (9.5 mm) aggregate.
- For use when grout space is greater than 4" (100 mm) in both directions.
- Available in 3000 lb. bulk bags



Self-Consolidating Core-Fill Grout Calculator				
Number of 8" x 8" x 16" Standard blocks	50	200	500	1000
Number of 80 lb. (36.3 kg) bags*	18	72	179	357
Number of 3000 lb. (1360.8 kg) bags*	1	2	5	10

* Amounts are estimated for filling all cells of standard block

