



Stucco and Mortar Color (Liquid)

No. 1319

PRODUCT DESCRIPTION

QUIKRETE® Stucco and Mortar Color is a liquid color additive for Stuccos, mortars and other cementitious systems.

Uses

QUIKRETE® Stucco and Mortar Color is used with QUIKRETE® Mortar Mix, Mason Mix, Glass Block Mortar, QUIKWALL® Surface Bonding Cement, QUIKRETE® Finish coat Stucco, QUIKWALL® Fiberglass Reinforced Stucco or Heavy Duty Masonry Coating. The color is added to the water before mixing into the dry QUIKRETE® product.

Features

QUIKRETE® Stucco and Mortar Color comes in 20 standard colors. Some of the colors require a gray base and some require a white base. Color charts are available which clearly describe which base to use to achieve a particular color. Color-coded bright attention package, easier to identify and inventory. Instructions on package aid customers in use and selection. Many merchandising advantages with better looking package. Bottles are shipped in a convenient display carton. Remove the kraft slipover carton and bottles are ready to display in an attractive yellow and white carton tray.

Packaging and Yield

QUIKRETE® Stucco and Mortar Color is packaged in 10 oz. (296 ml) bottles with a twist-off cap. Twelve (12) bottles are packed in each shipper carton. Each bottle of Stucco and Mortar Color is designed to be used with one bag of the recommended products.

Limitations:

This product is designed for mixing into cementitious systems at the time of their application. Under no circumstances is this product to be painted on the surface of hardened or partially hardened mortar or stucco.

The color chart is only an approximate representation of the color that will be achieved

with a particular product. It is recommended that a test panel be prepared prior to beginning the project. Depth of color will vary when using 60 lb (27.2 kg) vs 80 lb (36.3 kg) bags. For a deeper color use the 60 lb (27.2) bags. The uniformity of color cannot be guaranteed by the materials manufacturer. Color uniformity is affected by water quantity, thoroughness of mixing, cleanliness of equipment, application technique, curing conditions and curing procedure. Temperature, wind velocity, direct sunlight or shading, as well as the dampness or dryness of the surface receiving the material, have an effect on the finished depth of color.

Mixing:

Mix the color thoroughly with the mix water prior to adding the powder. Mix the powder in accordance with the instructions for the particular product being used. For maximum color uniformity be careful to use the same amount of pigment in each batch. Mix the next batch of product into the last half of the previous batch to even out any differences. Do not stop in the middle of a wall. Stop at joints or natural breaks in the building.

Warranty

The QUIKRETE® Companies warrant this product to be of merchantable quality when used or applied in accordance with the instructions or applied in accordance with the instructions herein. The product is not warranted as suitable for any purpose or use other than the general purpose for which it is intended. Liability under this warranty is limited to the replacement of its product (as purchased) found to be defective, or at the shipping companies' option, to refund the purchase price. In the event of a claim under this warranty, notice must be given to The QUIKRETE® Companies in writing at Atlanta, GA 30305. The limited warranty is issued and accepted in lieu of all other express warranties and expressly excludes liability for consequential damages.

The QUIKRETE® Companies, Inc.

One Securities Centre
3490 Piedmont Road, Suite 1300
Atlanta, GA 30305
404.634.9100