

COMMERCIAL GRADE QUIKRETE®

Concrete Mix Selector Guide



Concrete	General Use	Rapid Hardening Structural Concrete	High Strength Earlier	Resists Cracking & Spalling	Sets Post Without Mixing & Building
Attributes	<ul style="list-style-type: none"> Structural Concrete Mix Normal Set 	<ul style="list-style-type: none"> 1 Hour Working Time 3 Hour Walk-on Time Air Entrained Corrosion Resistant 	<ul style="list-style-type: none"> High Early Strength Gain 10 to 12 hr Walk-On Time 	<ul style="list-style-type: none"> Crack Resistant Air Entrained Improved Workability Normal Set 	<ul style="list-style-type: none"> Sets Posts without Mixing Sets in 20 to 40 Min.
Strengths	<ul style="list-style-type: none"> 4000 PSI @ 28 days 1500 PSI @ 3 days 	<ul style="list-style-type: none"> 6500 PSI @ 28 days 3000 PSI @ 24 hours 	<ul style="list-style-type: none"> 5000 PSI @ 28 days 1500 PSI @ 1 day 	<ul style="list-style-type: none"> 4000 PSI @ 28 days 1500 PSI @ 3 days 	<ul style="list-style-type: none"> 4000 PSI @ 28 days
ASTM	ASTM C 387	ASTM C 928 R-3	ASTM C 387	ASTM C 387	ASTM C 387
Applications					
Patios, Sidewalks, etc.	•	•	•	•	
Footings	•	•	•		
Driveway Aprons		•	•	•	
Cold Weather Use		•	•		
Setting Posts	•				•
Set Posts w/o Mixing					•
Steps	•	•	•	•	
Columns	•	•	•		
Walls	•	•	•		
Curbs	•	•	•	•	
Air Conditioner Pads	•	•		•	•
Floors	•	•	•	•	
Deck Supports	•	•	•		•
Bridge Deck Repairs		•			
Concrete Parking Lots		•		•	
Loading Docks		•	•		
Rapid Structural Repair		•			

For QUIKRETE® How-To Videos and Technical Data Sheets for all QUIKRETE® Commercial Grade products, visit www.quikrete.com