



**1. Product Name**

QUIKRETE® Concrete Acrylic Fortifier #8610

**2. Manufacturer**

The QUIKRETE Companies  
 One Securities Centre  
 3490 Piedmont Rd., NE, Suite 1300  
 Atlanta, GA 30305  
 (404) 634-9100  
 Fax: (404) 842-1424  
 www.quikrete.com

**3. Product Description**

**BASIC USE**

QUIKRETE Concrete Acrylic Fortifier is a highly water resistant acrylic resin formulation designed as a bonding agent admixture for thin Portland cement coatings. It densifies surfaces and makes them more resistant to many chemicals and mild acids, as well as to the penetration of water or aqueous solutions.

**Application With Repair Products**

For making thin repairs to concrete, use with QUIKRETE Sand Mix, Quick-Setting Cement and other repair materials. Mix QUIKRETE Concrete Acrylic Fortifier directly into the repair material as part of the liquid addition.

**Applications With Wall Products**

Use with QUIKWALL Surface Bonding Cement or Heavy Duty Masonry Coating in new construction or rehabilitation to achieve improved bond strength and to increase water resistance. QUIKWALL Surface Bonding Cement with Concrete Acrylic Fortifier is a good choice for rehabilitation of damaged concrete and masonry walls.

Use Concrete Acrylic Fortifier with QUIKRETE One Coat Fiberglass Reinforced Stucco (FRS) or Finish Coat Stucco to provide increased bond strength and curing properties, reduced shrinkage cracking and to prevent separation between basecoats and finish coats.

**Applications With Tile Products**

A 50:50 mixture of QUIKRETE Concrete Acrylic Fortifier and water is used with tile setting and grouting products to improve bond and water resistance.

**SIZES**

- 1 qt (0.95 L) plastic bottles
- 1 gal (3.8 L) plastic jugs

**LIMITATIONS**

- QUIKRETE Concrete Acrylic Fortifier is not to be used with polymer modified products
- Do not use with products containing air entrainment such as mortar mixes made from masonry cement
- Do not use in combination with Concrete Bonding Adhesive (#9902)

**4. Technical Data**

When added to the appropriate cementitious system, QUIKRETE Concrete Acrylic Fortifier will provide the following benefits compared to the unmodified system:

- Excellent toughness and good adhesion to clean stucco, concrete or masonry surfaces
- Reduced permeability to provide resistance to the penetration of salt water and other aggressive chemicals
- Reduced drying shrinkage which reduces the tendency for cracking and crazing in thin repairs
- Eliminates the need for moist curing under most circumstances
- Excellent water resistance to decrease spalling, cracking and surface degradation caused by repeated freeze/thaw cycles
- Suitable for use with trowel applied repair mortars and stuccos as well as sprayable systems such as QUIKWALL Surface Bonding Cement and QUIKRETE One Coat FRS
- One coat of QUIKWALL Surface Bonding Cement or 2 coats of QUIKRETE Heavy Duty Masonry Coating with Concrete Acrylic Fortifier added will meet most building code requirements for dampproofing concrete and masonry foundations

**5. Installation**

**SURFACE PREPARATION**

- It is absolutely necessary that all substrates be completely clean and free from dust, dirt, oil, wax and grease
- Previously painted surfaces must be stripped to ensure that all remaining paint is removed

**MIXING**

- Shake well before using
- Use the recommended amount of Concrete Acrylic Fortifier along with sufficient water to provide proper consistency
- For QUIKRETE Sand Mix, QUIKRETE One Coat FRS or Finish Coat Stucco, use 0.5 gal (1.9 L) of



QUIKRETE® Concrete Acrylic Fortifier #8610

- Concrete Acrylic Fortifier per 80 lb (36.3 kg) bag or 3 pints (1.4 L) per 60 lb (27.2 kg) bag
- For QUIKRETE Quick-Setting Cement and QUIKWALL Surface Bonding Cement, add 0.5 gal (1.9 L) of Concrete Acrylic Fortifier per 50 lb (22.7 kg) bag
- For QUIKRETE Heavy Duty Masonry Coating, use 0.5 gal (1.9 L) of Concrete Acrylic Fortifier per 40 lb (18.2 kg) bag

Note - QUIKRETE One Coat FRS Concentrated requires 1.5 gal (5.7 L) of Concrete Acrylic Fortifier per bag along with the appropriate amount of stucco sand.

**APPLICATION**

Apply in accordance with instructions for product being modified.

**CURING**

Under normal conditions, do not moist cure since air is essential in the curing of Concrete Acrylic Fortifier mixes; however, under extreme conditions of wind and heat, moist curing may be required for the first 24 hours.

**PRECAUTIONS**

- Store in a cool, dry place and protect product from freezing
- Do not place finishes or patches at temperatures below 50 degrees F (10 degrees C), or when temperatures are expected to fall below 40 degrees F (4 degrees C) within 24 hours
- Do not use with other polymer modified cementitious products



Note - It is extremely important that mixing proportions and directions are followed explicitly. Any deviations from mixing proportions that result in lesser quantities of Concrete Acrylic Fortifier could cause inadequate adhesion and performance.

**6. Availability**

QUIKRETE Concrete Acrylic Fortifier is available at leading concrete construction supply houses and distributors. Contact QUIKRETE Construction Products for the name of the nearest dealer.

**7. Warranty**

The QUIKRETE Companies warrant this product to be of merchantable quality when used or applied in accordance with the instructions herein. The product is not warranted as suitable for any purpose or use other than the general purpose for which it is intended. Liability under this warranty is limited to the replacement of its product (as purchased) found to be defective or, at the shipping companies' option, to refund the purchase price. In the event of a claim under this warranty, notice must be given to The QUIKRETE Companies in writing. This limited warranty is issued and accepted in lieu of all other express warranties and expressly excludes liability for consequential damages.

**8. Maintenance**

None required.

**9. Technical Services**

The QUIKRETE Companies maintain technical field representatives throughout the country. Contact a local distributor for the name and number of the nearest representative or call QUIKRETE Construction Products.

**10. Filing Systems**

Additional product information is available from the manufacturer.